

PRODUCT DATA SHEET

Casco® Cascol Indoor

Fast setting Interior wood adhesive

DESCRIPTION

Casco® Cascol Indoor is a fast setting wood adhesive for interior use with short pressing time and long shelf life.

USES

Casco® Cascol Indoor is designed for joint- and assembly gluing as well as carpentry and furniture on applications where water resistance is not required.

Casco® Cascol Indoor could be exposed to occasional short-term running or condensed water or high humidity.

Casco® Cascol Indoor is suitable for gluing of hard or difficult wood.

FEATURES

- Short pressing time
- Hard glue line with low creep
- Especially good adhesion to hard and exotic wood
- Long shelf life
- Joint resistant to broad temperature range

CERTIFICATES AND TEST REPORTS

- FprEN 204 D2/2

PRODUCT INFORMATION

Composition	PVAC dispersion
Packaging	100, 300 and 750 ml bottles
Colour	White with an opaque glueline
Shelf life	Casco® Cascol Indoor has a shelf life of 24 months from the date of production, if stored properly in undamaged, original, sealed packaging, and if the storage conditions are met.
Storage conditions	Casco® Cascol Indoor shall be stored in dry conditions, protected from direct sunlight and at temperatures between +5 °C and +30 °C.
Density	~1.08 kg/l
Consistency	Viscous
Solid content by mass	~47 %

TECHNICAL INFORMATION

Shear strength	~9.3 N/mm ²	(FprEN 205)
Service temperature	+10 °C min. / +70 °C max.	

APPLICATION INFORMATION

Consumption	60–200 g/m ²
Open Time	~5 min. max. (beech / beech, 23 °C)
Pressing time	~10 min. max. (beech / beech, 23 °C)

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTATION

- Safety Data Sheet

IMPORTANT CONSIDERATIONS

- The wood shall contain less than 15 % moisture.
- Sand off any excess adhesive before staining the wood.
- Do not use Casco® Cascol Indoor at temperatures below +10 °C.
- Do not use Casco® Cascol Indoor in areas with permanent moisture or condensate.
- Do not use Casco® Cascol Indoor for permanent water immersion.
- Do not use Casco® Cascol Indoor for load bearing constructions.
- Do not over apply Casco® Cascol Indoor since this would slow down the curing.
- When gluing oak, the tannin might react with components present in the adhesive causing discoloration. To avoid such problems a pretest shall be made.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

For the application of Casco® Cascol Indoor all generally accepted rules of building and construction apply.

SUBSTRATE PREPARATION

The substrate must be clean, dry, sound and homogeneous, free from oils, grease, dust and loose or friable particles. Casco® Cascol Indoor adheres without primers and/or activators. The moisture content of the wood should be in the range of 5–14 %, preferably 7–10 %.

APPLICATION METHOD / TOOLS

After the necessary substrate preparation, shake the bottle well before the application. Apply Casco® Cascol Indoor with a brush, toothed trowel or roller on one wood surface. When gluing hardwood and exotic

wood, Casco® Cascol Indoor is applied on both bonding surfaces. Do not over apply since this would slow down the curing.

Join the corresponding surfaces and apply a pressure of ~0.5–1.0 MPa within 10 minutes. Clean excess glue after clamping with a damp cloth.

Softwood substrates (e.g. pine) required a pressing time of ~10–15 minutes at 23 °C. Hardwood substrates (e.g. oak or teak) require a longer pressing time. Large bond areas require a longer pressing time as well.

The origin, type and moisture content of the wood as well as ambient conditions like temperature and humidity will affect both the open- and pressing time. When fitting dowels, the glue should be applied into the holes.

CLEANING OF EQUIPMENT

Clean all tools and application equipment immediately after use with a damp cloth. Once cured, residual material can only be removed mechanically or with methanol.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recom-

mended, unless stated otherwise.

Sika Danmark A/S
Hirsemarken 5
3520 Farum
Tlf. +45 48 18 85 85
www.sika.dk



PRODUCT DATA SHEET
Casco® Cascol Indoor
April 2025, Version 01.01
020513030000000078

CascoCascolIndoor-en-DKCASCO-(04-2025)-1-1.pdf